



Adaptive Cruise Control Radar Performance Test

OEM Bumper Coated With Ngenco Paint Protection Spray (PPS)

Unit 4, West Court, Buntsford Park Road, B60 3DX Email: technical@ngenco.com Website: ngenco.com



Report on the Radio Testing

for

Ngenco

Limited

on

Processed Car Bumper Pieces

Report no. TRA-049966-45-00A

16 March 2020

RF908 7.0

Element Materials Technology Warwick Ltd. Registered in England and Wales. Registered Office: 5 Fleet Place, London, EC4M 7RD Company Reg No. 02536659



Report Number: TRA-049966-45-00A Issue: A

REPORT ON THE RADIO TESTING OF A Ngenco Ltd Processed Car Bumper Pieces

ABSORPTION CHARACTERISTICS ON 76 GHz CW SIGNAL

TEST DATE: 2020-03-05

Alan Wmg.

Digitally signed by A Wong DN:cn=AWong,o=ElementMaterials Technology Warwick Ltd., ou, email=alan.wong@element.com, c=GB Date: 2020.03.16 16:36:30 Z

A. L. Y. Wong Radio Test Engineer

John Charters

J. Charters Lab Manager

Approved by:

Written by:

Date:

16 March 2020

Disclaimers:

[1] THIS DOCUMENT MAY BE REPRODUCED ONLY IN ITS ENTIRETY AND WITHOUT CHANGE [2] THE RESULTS CONTAINED IN THIS DOCUMENT RELATE ONLY TO THE ITEM(S) TESTED

RF908 7.0

Element Materials Technology Warwick Ltd. Registered in England and Wales. Registered Office: 5 Fleet Place, London, EC4M 7RD Company Reg No. 02536659

1 Revision Record

Issue Number	Issue Date	Revision History
A	16 March 2020	Original

2 Summary

TEST REPORT NUMBER:	TRA-049966-45-00A
WORKS ORDER NUMBER:	TRA-049966-01
PURPOSE OF TEST:	Measurement of RF power absorption by samples
EQUIPMENT UNDER TEST (EUT):	Processed Car Bumper Pieces
MANUFACTURER/AGENT:	Ngenco Ltd
ADDRESS:	West Court Bromsgrove B60 3DX United Kingdom
	Ngenco Limited ■ +44 (0) 1527 570077 ✓ <u>technical@ngenco.com</u>
ORDER NUMBER:	PO:6998
TEST DATE:	2020-03-05
TESTED BY:	A. L. Y. Wong Radio Test Engineer Element

2.1 Test Summary

Test Method and Description	Requirements	Applicable
Absorption of 76 GHz continuous wave	As requested by the client	\boxtimes

Notes:

The results contained in this report relate only to the items tested, in the condition at time of test, and were obtained in the period between the date of initial receipt of samples and the date of issue of the report.

The apparatus was set up and exercised using the configurations, modes of operation and arrangements defined in this report only. Any modifications made are identified in Section 8 of this report.

Particular operating modes, apparatus monitoring methods and performance criteria required by the standards tested to have been performed except where identified in Section 5.2 of this test report (Deviations from Test Standards).

3 Contents

 Revision Record Summary 	
2.1 Test Summary	5
3 Contents	
4 Introduction	7
5 Test Specifications	
5.1 Normative References	8
6 Glossary of Terms	9
7 Equipment Under Test	
7.1 EUT Identification	
7.2 System Equipment	
7.3 EUT Parameters	
7.4 EUT Description	
8 Photographs	
9 RF Signal Attenuation	
9.1 Definition	
9.2 Test Parameters	
9.3 Radiated Measurement	
9.3.1 Test Method	
9.3.2 Test Equipment	
9.3.3 Test Results	15

4 Introduction

 \times

This report TRA-049966-45-00A presents the results of the Radio testing on a Ngenco Ltd, Processed Car Bumper Pieces for absorption characteristics of 76 GHz continuous wave.

The testing was carried out for Ngenco Ltd by Element, at the address detailed below.

Element HullElement SkelmersdaleUnit EUnit 1South Orbital Trading ParkPendle PlaceHedon RoadSkelmersdaleHullWest LancashireHU9 1NJWN8 9PNUKUK

This report details the configuration of the equipment, the test methods used and any relevant modifications where appropriate.

All test and measurement equipment under the control of the laboratory and requiring calibration is subject to an established programme and procedures to control and maintain measurement standards. The quality management system meets the principles of ISO 9001, and has quality control procedures for monitoring the validity of tests undertaken. Records and sufficient detail are retained to establish an audit trail of calibration records relating to its test results for a defined period. Under control of the established calibration programme, key quantities or values of the test & measurement instrumentation are within specifications, which are UKAS calibrated as such where these properties have a significant effect on results. Participation in inter-laboratory comparisons and proficiency testing ensures satisfactory correlation of results conform to Elements own procedures, as well as statistical techniques for analysis of test data providing the appropriate confidence in measurements.

5 Test Specifications

5.1 Normative References

• Specific test requirements and methods to investigate the amount of RF power absorbed by the samples when 76 GHz continuous wave signals propagated through them.

6 Glossary of Terms

7 Equipment Under Test

7.1 EUT Identification

• Name: Processed Car Bumper Pieces

7.2 System Equipment

Equipment listed below forms part of the overall test setup and is required for equipment functionality and/or monitoring during testing. The compliance levels achieved in this report relate only to the EUT and not items given in the following list.

Not Applicable – No support/monitoring equipment required.


7.3 EUT Parameters

Sample:	Cut-outs from a modern automotive bumper	
Process:	Sanding	
Coating:	Ngenco CPPS	


7.4 EUT Description


The EUT are pieces of car bumper, with different processes and treatments.

Photographs 8



The following photographs shows basic EUT set-up:





9 RF Signal Attenuation

9.1 Definition

The RF power absorbed by the material.

9.2 Test Parameters

Test Location:	Element Hull
Test Chamber:	Wireless Laboratory 2
Frequency Measured:	76 GHz
Measurement BW:	1 MHz
Measurement Detector:	RMS

Environmental Conditions (Normal Environment)

Radiated

Temperature: 23 °C	Standard Requirement: +15 °C to +35 °C
Humidity: 33 %RH	Standard Requirement: 20%RH to 75%RH

9.3 Radiated Measurement

9.3.1 Test Method

With the EUT setup as per section 9 of this report and connected as per Figure ix, the testing of the level of attenuation of four bumper samples was performed.

1. A test bed was used, consisting of a 76 GHz CW transmitter and a tuned receiver to measure received signal strength in a controlled environment (semi-anechoic chamber), with space between the two antennas to insert the bumper samples. Separation between bumper sample and each antenna was ≈50 mm unless otherwise specified in writing.


2. The system was calibrated to give a known received signal strength at 76 GHz with no bumper sample present and this figure was recorded.


3. A bumper sample was inserted between the two antennas and the received signal strength was measured to obtain attenuation result.

4. The received signal strength at 76 GHz with no bumper sample present was measured again to ensure consistency and this figure was recorded.

5. Steps 2, 3 and 4 was repeated again for each of the different samples.

Figure ix Test Setup





Sample

9.3.2 Test Equipment

Equipment		Equipment	Element	Due For
Description	Manufacturer	Туре	No	Calibration
Spectrum Analyser	Agilent	N9030A	REF2167	2020-08-12
Signal Generator	Agilent	PSG E8257D	REF2168	2020-12-09
75-110 GHz	FM Ltd	Horn Antenna	REF2214	Cal. before use
6x W-band	MI-WAVE	Mixer	REF2211	Cal. before use
K-Type RF coaxial cable	Teleydyne	Cable	REF2185	Cal. before use
75-110 GHz	Agilent	Mixer	TRLUH367	Cal. before use

9.3.3 Test Results

	Arb	RF Power		
Sample	Before (no sample)	Sample Present	After (no sample)	Absorbed (dBm)
1	-52.0	-52.9	-52.0	0.9
2	-51.8	-53.2	-51.8	1.4
3	<mark>-52.2</mark>	<mark>-53.3</mark>	<mark>-52.2</mark>	<mark>1.1</mark>
4 (Simulated rain on 1)	-52.1	-53.7	-52.1	1.6

KEY: Four samples of cut-outs from a modern automotive bumper with different treatments

1. "Control" sample, as from the production line.

2. "Repaired" sample, as from the production line and then sanded, primed, and repainted.

3. "Triple coated" sample, as from the production line and treated with Ngenco PPS anti-chip coating, then repainted, then treated again with Ngenco stage 3 anti-chip coating.

4. "Simulated rain" sample, made by spraying "Control" sample with de-ionized water to simulate rain spray.

Unit 4, West Court, Buntsford Park Road, B60 3DX Email: technical@ngenco.com Website: ngenco.com